
WILKINSON HEAVY PRECAST LIMITED

DUNDAS, ONTARIO

www.wilkinsonheavyprecast.com

905-628-5611



Commensurate with a **2 Metre** burial over the top slab in firm soil under an area of vehicular traffic.

For recommended installation procedures refer to Wilkinson Installation Guidelines and Lifting and Assembly Instructions.

PRECAST UTILITY MANHOLE MODEL U73

CONSTRUCTION DETAILS *

- Concrete: 35 MPa at 28 Days, 5 to 8% Air Entrainment. Precast concrete
- Reinforcing: 15 M bars at 150 mm centres each way in roof, walls and floor.